




GRABO

1905

Evidence 60

Technical datasheet

Entertainment

Technical parameter	Standard	Unit	Result
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	6,0
Wear layer thickness	EN ISO 24340	mm	0,7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	15/20
Total weight	EN ISO 23997	kg/m ²	3,3
Residual indentation	EN ISO 24343	max. mm	0,2
Dimensional stability	EN ISO 23999	max. %	±0,2
Curling	EN ISO 23999	max.mm	8
Reaction to fire	EN 13501-1	class	Cfl-s1
Abrasion group	EN 660-1	group	T
Light fastness	EN ISO 105-B02	grade	>6
Chemical resistance	EN ISO 26987	-	high resistance
Slip resistance	EN 13893	class	DS
Castor chair resistance	ISO 4918 / EN 425		slight change
Surface treatment			CLP
Antibacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
Warranty		year	temporary: 2 permanent: 7
CE MARKING	EN 14041		✓

GRABOPLAST Ltd.

H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
info@grabo1905.com www.grabo1905.com