




GRABO

1905

Grabolett

Technical datasheet

Entertainment

| Technical parameter | Standard | Unit | Result |
|--------------------------------------|---|-------------------|--------------------------------------|
| Construction | | | compact heterogeneous |
| Total thickness | EN ISO 24346 | mm | 1,7 |
| Wear layer thickness | EN ISO 24340 | mm | 0,7 |
| Width of roll | EN ISO 24341 | m | 2 |
| Length of roll | EN ISO 24341 | lm | 20 |
| Total weight | EN ISO 23997 | kg/m ² | 2,1 |
| Residual indentation | EN ISO 24343 | max. mm | 0,1 |
| Dimensional stability | EN ISO 23999 | max. % | ±0,2 |
| Curling | EN ISO 23999 | max. mm | 8 |
| Reaction to fire | EN 13501-1 | class | Bfl-s1 |
| Abrasion group | EN 660-1 | group | T |
| Light fastness | EN ISO 105-B02 | grade | > 6 |
| Chemical resistance | EN ISO 26987 | - | high resistance |
| Slip resistance | EN 13893 | class | DS |
| Castor chair resistance | ISO 4918 / EN 425 | | slight change |
| Surface treatment |  | | CLP |
| Antibacterial and fungicid treatment |  | | graboSAN |
| Enviromental attributes |  | | Solvent and heavy metal free product |
| Warranty | | year | 3 |
| CE MARKING | EN 14041 | | ✓ |

GRABOPLAST Ltd.

H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
 info@grabo1905.com www.grabo1905.com