



GRABO

1905

JP 25

Technical datasheet

TRANSPORT

Technical parameter	Standard	Unit	Result
Construction			Heterogeneous
Thickness	EN ISO 24346	mm	2,7
Wear layer	EN ISO 24340	mm	0,5
Length of rolls	EN ISO 24341	m	21
Width	EN ISO 24341	m	1,4; 2
Weight	EN ISO 23997	kg/m ²	2,6
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max. %	±0,4
Light fastness	EN ISO 105-B02	grade	6
Abrasion group	EN 660-2	group	T
Reaction to fire	EN 13501-1	class	Cfl-s1
Slip resistance	EN 13893	class	DS
Chemical resistance	EN ISO 26987	-	high resistance
Castor chair resistance	ISO 4918 / EN 425		slight change
Antibacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and Heavy metal free product
Seaming method			Heat welding
Warranty			7 years
CE MARKING	EN 14041		✓

GRABOPLAST Floor Covering Manufacturers Ltd.
H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
mail@graboplast.hu www.graboplast.hu